

HOMOGENEOUS PHASE OF COEXISTENCE OF SPIN-TRIPLET SUPERCONDUCTIVITY AND FERROMAGNETISM

D. V. SHOPOVA* and D. I. UZUNOV

*CPCM Laboratory, G. Nadjakov Institute of Solid State Physics,
Bulgarian Academy of Sciences, BG-1784 Sofia, Bulgaria.*

* Corresponding author: sho@issp.bas.bg

Key words: superconductivity, ferromagnetism, phase diagram,
order parameter profile.

PACS: 74.20.De, 74.20.Rp

Abstract

The coexistence of a homogeneous (Meissner-like) phase of spin-triplet superconductivity and ferromagnetism is investigated within the framework of a phenomenological model of spin-triplet ferromagnetic superconductors. The results are discussed in view of application to metallic ferromagnets as UGe_2 , ZrZn_2 , URhGe , and Fe.

1. Introduction

Experiments at low temperatures and high pressure have indicated a coexistence of ferromagnetism and superconductivity in the metallic compounds UGe_2 [1, 2, 3], ZrZn_2 [4], URhGe [5] and also in Fe [6]. In contrast to other superconducting materials (see, e.g., Refs. [7, 8]), in these metals the phase transition temperature to the ferromagnetic state is higher than the phase transition temperature to the superconducting state and the superconductivity not only coexists with the ferromagnetic order but is enhanced by it. It is widely accepted [1, 10] that this superconductivity can be most naturally understood as a spin-triplet rather than a spin-singlet pairing phenomenon (see, e.g., Ref. [9]). The experiments [6] on high-pressure crystal modification of Fe, which has a hexagonal closed-packed structure, are also interpreted [1] in favour of the appearance of same unconventional superconductivity. Note, that both vortex and Meissner superconductivity phases [6] are found in the high-pressure crystal modification of Fe where the strong ferromagnetism of the usual bcc iron crystal probably disappears [10].

The phenomenological theory that explains coexistence of ferromagnetism and unconventional spin-triplet superconductivity of Landau-Ginzburg type was derived [11, 12] on the

basis of general symmetry group arguments . It describes the possible low-order coupling between the superconducting and ferromagnetic order parameters and establishes several important features of the superconducting vortex state in the ferromagnetic phase of unconventional ferromagnetic superconductors [11, 12]. Both experimental and theoretical problems of the ferromagnetism in spin-triplet superconductors seem to be quite different from those in conventional (s-wave) ferromagnetic superconductors [7, 8].

In this letter we investigate the conditions for the occurrence of the homogeneous (Meissner-like) phase of coexistence of spin-triplet superconductivity and ferromagnetism. Such a phase of coexistence may occur at relatively small magnetization and at zero external magnetic field. Taking in mind this circumstance and using model considered in Refs. [11, 12] we show that the phase transition to the superconducting state in ferromagnetic superconductors can be either of first or second order and this depends on the model parameters that correspond to the particular substance. Our investigation is based on the mean-field approximation [13] as well as on familiar results about the possible phases in nonmagnetic superconductors with triplet (*p*-wave) Cooper pairs [14, 15]. We neglect all anisotropies, usually given by the respective additional Landau invariants and gradient terms [9] in the Ginzburg-Landau free energy of unconventional superconductors. The reason is that the inclusion of crystal anisotropy is related with lengthy formulae and a multivariant analysis which will obscure our main aims and results. Let us emphasize that the present results should be valid in the same or modified form when the crystal anisotropy is properly taken into account. We have to mention also that there is a formal similarity between the phase diagram obtained in our investigation and the phase diagram of certain improper ferroelectrics [16].

2. Model

We consider the Ginzburg-Landau free energy [11, 12] $F = \int d^3x f(\psi, \vec{\mathcal{M}})$, where

$$f = \frac{\hbar^2}{4m}(D_j^*\psi)(D_j\psi) + a_s|\psi|^2 + \frac{b}{2}|\psi|^4 + a_f\vec{\mathcal{M}}^2 + \frac{\beta}{2}\mathcal{M}^4 + i\gamma_0\vec{\mathcal{M}}.(\psi \times \psi^*) . \quad (1)$$

In Eq. (1), $D_j = (\nabla - 2ieA_j/\hbar c)$, and A_j ($j = 1, 2, 3$) are the components of the vector potential $\vec{A}$ related with the magnetic induction $\vec{B} = \nabla \times \vec{A}$. The complex vector $\psi = (\psi_1, \psi_2, \psi_3) \equiv \{\psi_j\}$ is the superconducting order parameter, corresponding to the spin-triplet Cooper pairing and $\vec{\mathcal{M}} = \{\mathcal{M}_j\}$ is the magnetization. The coupling constant $\gamma_0 = 4\pi J > 0$ is given by the ferromagnetic exchange parameter ($J > 0$). Coefficients $a_s = \alpha_s(T - T_s)$ and $a_f = \alpha_f(T - T_f)$ are expressed by the positive parameters α_s and α_f as well as by the superconducting (T_s) and ferromagnetic (T_f) critical temperatures in the decoupled case, when $\mathcal{M}\psi_i\psi_j$ -interaction is ignored; $b > 0$ and $\beta > 0$ as usual.

We assume that the magnetization $\mathcal{M}$ is uniform, which is a reliable assumption outside a quite close vicinity of the magnetic phase transition but keep the spatial ($\vec{x}$ -) dependence of ψ . The reason is that the relevant dependence of ψ on $\vec{x}$ is generated by the diamagnetic effects arising from the presence of $\mathcal{M}$ and the external magnetic field $\vec{H}$ [11, 12] rather

than from fluctuations of ψ (this effect is extremely small and can be safely ignored). First term in (1) will be still present even for $\vec{H} = 0$ because of the diamagnetic effect created by the magnetization $\vec{\mathcal{M}} = \vec{B}/4\pi > 0$. As we shall investigate the conditions for the occurrence of the Meissner phase where ψ is uniform, the spatial dependence of ψ and, hence, the first term in r.h.s. of (1) will be neglected. This approximation should be valid when the lower critical field $H_{c1}(T)$ is greater than the equilibrium value of the magnetization $\mathcal{M}$ in the phase of coexistence of superconductivity and ferromagnetism.

One may take advantage of the symmetry of model (1) and avoid the consideration of equivalent thermodynamic states that occur as a result of the respective continuous symmetry breaking at the phase transition point but have no effect on thermodynamics of the system. We shall assume that the magnetization vector is along the z -axis: $\vec{\mathcal{M}} = (0, 0, \mathcal{M})$, where $\mathcal{M} \geq 0$. We find convenient to use the following notations: $\varphi_j = b^{1/4}\psi_j$, $\varphi_j = \phi_j \exp(\theta_j)$, $M = \beta^{1/4}\mathcal{M}$, $\gamma = \gamma_0/(b^2\beta)^{1/4}$, $r = a_s/\sqrt{b}$, $t = a_f/\sqrt{\beta}$, $\phi^2 = (\phi_1^2 + \phi_2^2 + \phi_3^2)$, and $\theta = (\theta_2 - \theta_1)$.

We shall not dwell on the metastable and unstable phases described by the model (1) [17] as well as on the vortex phase [11, 12] corresponding to $|\vec{B}| > H_{c1}$. Rather we consider the stable homogeneous phases at zero external magnetic field ($\vec{H} = 0$) that are described by uniform order parameters $\mathcal{M}$ and ψ . We shall essentially use the condition $T_f > T_s$.

3. Results and discussion

The model (1) describes three stable homogeneous phases: (1) normal phase ($\phi_j = M = 0$) (hereafter referred to as N-phase), (2) ferromagnetic (FM-) phase ($\phi_j = 0$, $M^2 = -t > 0$), and (3) a phase of coexistence of superconductivity and ferromagnetism (FS-phase), given by $\phi_3 = 0$, $\theta = 2\pi(k - 1/4)$, ($k = 0, \pm 1, \dots$), $\phi^2 = (-r + \gamma M) > 0$, $6M^2 > (\gamma^2 - 2t)$, and

$$\frac{\gamma r}{2} = \left(\frac{\gamma^2}{2} - t \right) M - M^3. \quad (2)$$

It is not difficult to determine the domains of existence and stability of the phases N, FM, and FS. Note, that here we use the term “condition of stability” to indicate the necessary condition of stability when the respective phase corresponds to a minimum of the free energy, i.e., in both cases of stable and metastable states. When a phase corresponds to a global minimum of the free energy (a sufficient condition of stability) it will be called a “stable phase.” Thus we easily find the following existence and stability regions: ($t > 0$, $r > 0$) for the N-phase, ($t < 0$, $r > \gamma M$) - for FM. In order to obtain the same domain for FS one should consider Eq. (2) together with the additional existence and stability conditions corresponding to this phase: $\gamma M > r$ and $3M^2 > M_0^2$, where $M_0 > 0$ is defined by the $r(M) = 0$; see Eq. (2).

Eq. (2) is shown in Fig. 1 for $\gamma = 1.2$ and $t = -0.2$. For any $\gamma > 0$ and t , the stable FS thermodynamic states are given by $r(M) < r_m = r(M_m)$ for $M > M_m > 0$, where M_m corresponds to the maximum of the function $r(M)$. Functions $M_m(t)$ and $M_0(t) = (-t + \gamma^2/2)^{1/2} = \sqrt{3}M_m(t)$ are drawn in Fig. 2 for $\gamma = 1.2$. Functions $r_m(t) = 4M_m^3(t)/\gamma$




Figure 1: $h = \gamma r/2$ as a function of M for $\gamma = 1.2$, and $t = -0.2$.

for $t < \gamma^2/2$ (the line of circles in Fig. 3) and $r_e(t) = \gamma|t|^{1/2}$ for $t < 0$ (the dotted in Fig. 3) define the borderlines of existence and stability of FS.

In the region on the left of the point B (Fig. 3) with coordinates $(-\gamma^2/4, \gamma^2/2)$, FS satisfies the existence condition $\gamma M > r$ only below the dotted line [$r < r_e$]. In the domain confined between the lines of circles and the dotted line on the left of the point B the stability condition for FS is satisfied but the existence condition is broken. The inequality $r \geq r_e(t)$ is the stability condition of FM for $0 \leq (-t) \leq \gamma^2/4$. For $(-t) > \gamma^2/4$ the FM phase is stable for all $r \geq r_e(t)$. The dotted line on the left of the point B, i.e. for $(-t) > \gamma^2/4$, is a line of the second order FM-FS phase transition. On this line the equilibrium order parameters are given by $\phi_j = 0$ and $M_{eq} = \sqrt{|t|}$. Therefore, the phase diagram for $(-t) > \gamma^2/4$ is clarified for any r . When $r < 0$ the FS phase is stable and is described by the function $r(M)$ for $M > M_0$, as shown in Fig. 3.

The part of the t -axis given by $r = 0$ and $t > \gamma^2/2$ in Fig. 3 is a phase transition line of second order that describes the N-FS transition. The same transition for $0 < t < \gamma^2/2$ is represented by the solid line AC which is the equilibrium transition line of a first order phase transition. This equilibrium transition curve is given by the function

$$r_{eq}(t) = \frac{1}{4} [3\gamma - (\gamma^2 + 16t)^{1/2}] M_{eq}(t), \quad (3)$$

where

$$M_{eq}(t) = \frac{1}{2\sqrt{2}} [\gamma^2 - 8t + \gamma (\gamma^2 + 16t)^{1/2}]^{1/2} \quad (4)$$

is the equilibrium value (jump) of the magnetization. The order of the N-FS transition




Figure 2: M versus t for $\gamma = 1.2$: the dashed line represents M_0 , the solid line represents M_{eq} , and the dotted line corresponds to M_m .




Figure 3: The phase diagram in the plane (t, r) with two tricritical points (A and B) and a triple point C ; $\gamma = 1.2$.

changes at the tricritical point A.

The domain above the solid line AC and below the line of circles for $t > 0$ is the region of a possible overheating of FS. The domain of overcooling of the N-phase is confined by the solid line AC and the axes ($t > 0, r > 0$). At the triple point C with coordinates $[0, r_{eq}(0) = \gamma^2/4]$ the phases N, FM, and FS coexist. For $t < 0$ the straight line

$$r_{eq}^*(t) = \frac{\gamma^2}{4} + |t|, \quad -\gamma^2/4 < t < 0, \quad (5)$$

describes the extension of the equilibrium phase transition line of the N-FS first order transition to negative values of t . For $t < (-\gamma^2/4)$ the equilibrium phase transition FM-FS is of second order and is given by the dotted line on the left of the point B (the second tricritical point in this phase diagram). Along the first order transition line $r_{eq}^*(t)$, given by (5), the equilibrium value of M is $M_{eq} = \gamma/2$, which implies an equilibrium order parameter jump at the FM-FS transition equal to $(\gamma/2 - \sqrt{|t|})$. On the dotted line of the second order FM-FS transition the equilibrium value of M is equal to that of the FM phase ($M_{eq} = \sqrt{|t|}$). At the triple point C the phases N, FM, and FS coexist.

In conclusion, we have demonstrated that the model (1) of ferromagnetic spin-triplet superconductors gives a quite complex phase diagram containing three ordered phases, two types of phase transitions, and two tricritical points, and a triple point. Further considerations of the effect of additional terms in the free energy (1) such as terms of the type $\vec{\mathcal{M}}^2|\psi|^2$ and/or terms describing the Cooper pair and crystal anisotropy [9, 14] may give more information about the shape of the phase diagram outlined in the present paper.

Acknowledgments: DIU thanks the hospitality of MPI-PKS-Dresden. Financial support through *Scenet* (Parma) and collaborative project with JINR-Dubna is also acknowledged.

References

- [1] S. S. Saxena, P. Agarwal, K. Ahilan, F. M. Grosche, R. K. W. Haselwimmer, M.J. Steiner, E. Pugh, I. R. Walker, S.R. Julian, P. Monthoux, G. G. Lonzarich, A. Huxley, I. Sheikin, D. Braithwaite, and J. Flouquet, *Nature* (London) **406**, 587 (2000).
- [2] A. Huxley, I. Sheikin, E. Ressouche, N. Kernavanois, D. Braithwaite, R. Calemczuk, and J. Flouquet, *Phys. Rev. B* **63**, 144519-1 (2001).
- [3] N. Tateiwa, T. C. Kobayashi, K. Hanazono, A. Amaya, Y. Haga, R. Settai, and Y. Onuki, *J. Phys. Condensed Matter* **13**, L17 (2001).
- [4] C. Pfleiderer, M. Uhlatz, S. M. Hayden, R. Vollmer, H. v. Löhneysen, N. R. Berhoeft, and G. G. Lonzarich, *Nature* (London) **412**, 58 (2001).
- [5] D. Aoki, A. Huxley, E. Ressouche, D. Braithwaite, J. Flouquet, J-P. Brison, E. Lhotel, and C. Paulsen, *Nature* (London) **413**, 613 (2001).
- [6] K. Shimizu, T. Kimura, S. Furomoto, K. Takeda, K. Kontani, Y. Onuki and K. Amaya, *Nature* (London) **412**, 316 (2001).
- [7] E. I. Blount and C. M. Varma, *Phys. Rev. Lett.* **42**, 1079 (1979).
- [8] T. K. Ng and C. M. Varma, *Phys. Rev. Lett.* **78**, 330 (1997).
- [9] V. P. Mineev, K. V. Samokhin, *Introduction to Unconventional Superconductivity* (Gordon and Breach, Amsterdam, 1999).
- [10] S. S. Saxena and P. B. Littlewood, *Nature* (London) **412**, 290 (2001).
- [11] K. Machida and T. Ohmi, *Phys. Rev. Lett.* **86**, 850 (2001).
- [12] M. B. Walker and K. V. Samokhin, *Phys. Rev. Lett.* **88**, 204001-1 (2002).
- [13] D. I. Uzunov, *Theory of Critical Phenomena* (World Scientific, Singapore, 1993).
- [14] E. J. Blagoeva, G. Busiello, L. De Cesare, Y. T. Millev, I. Rabuffo, and D. I. Uzunov, *Phys. Rev. B* **40**, 7321 (1990).
- [15] D. I. Uzunov, in: *Advances in Theoretical Physics*, ed. by E. Caianiello (World Scientific, Singapore, 1990) p. 96.
- [16] Yu. M. Gufan and V. I. Torgashev, *Sov. Phys. Solid State* **22**, 951 (1980) [*Fiz. Tv. Tela* (Leningrad) **22**, 1629 (1980)].
- [17] D. V. Shopova and D. I. Uzunov, *Phys. Lett. A* (2003) in press.